

Claims

1. Surface coated manganese sulfide, obtainable in that powdered manganese sulfide is provided, a coating agent, preferably selected from the group consisting of a wax, an ester of an inorganic or organic acid, an oil, a low-melting polymer, a mono- to multi-functional aliphatic alcohol with 2 to 12 carbon atoms or mixtures thereof, is added in an amount of 0.01 to 10 wt.% relative to the weight of the manganese sulfide used, and the mixture is mixed for a period of time which is sufficient to ensure a homogeneous mixture.
2. Manganese sulfide according to claim 1, characterized in that the powdered manganese sulfide has a particle size of 1 to 200 μm , preferably 1 to 10 μm .
3. Manganese sulfide according to claim 1 or 2, characterized in that the low melting polymer has a melting point under 150°C and is a polyester, polyamide or a polyaliphatic compound.
4. Manganese sulfide according to claim 1 and 2, characterized in that the ester of the inorganic acid is a phosphoric acid ester.
5. Manganese sulfide according to claim 4, characterized in that the phosphoric acid ester is diphenylcresylphosphate or triphenylphosphate.
6. Manganese sulfide according to claim 1 or 2, characterized in that the oil is a paraffinic oil or silicon oil.
7. Method for producing surface-modified manganese sulfide (MnS), characterized in that powdered manganese sulfide is provided, a coating agent, selected from the group consisting of a wax, an ester of an inorganic or an organic acid, an oil, a low melting polymer, a mono- to multi-functional aliphatic alcohol with 2 to 12 carbon atoms or mixtures

09830888-120501

thereof, is added in an amount of 0.01 to 10 wt.% relative to the weight of the manganese sulfide used, and the mixture is mixed for a period of time which is sufficient to ensure a homogeneous mixture.

5

8. Method according to claim 7, characterized in that the manganese sulfide has a particle size from 1 to 200 μm , probably from 1 to 10 μm .

10

9. Method according to claim 7 or 8, characterized in that the coating agent is added in an amount of 0.01 to 5.0 wt.%, especially preferably from 1.0 to 3.0 wt.%, relative to the weight of the manganese sulfide used.

15

10. Method according to any of the claims 7 to 9, characterized in that the ester of the inorganic acid is a phosphoric acid ester.

20

11. Method according to claim 10, characterized in that the ester of the phosphoric acid is diphenylcresylphosphate or triphenylphosphate.

25

12. Use of the manganese sulfide according to any of the claims 1 to 6 as an additive for improving the compression characteristics of powder mixtures.

30

13. Use of the manganese sulfide according to any of claims 1 to 6 as an additive to sinter powders for improving the processability of the molded sintered article.

35

14. Sinter powder, characterized by a content of manganese sulfide according to one of the claims 1-6.

15. Method for producing a molded article using the sinter powder according to claim 14, comprising the following steps:

- a) compression of the sinter powder in a sinter mold that has an inner shape corresponding to the final contour of the finished molded article;

D9830888-120501

- b) heating the green compact to a temperature above the evaporation temperature of the coating agent used for production of the manganese-sulfide and, if necessary, maintaining the green compact at this temperature for a period of time sufficient to ensure complete evaporation of the coating agent;
- c) sintering the green compact of step b);
- d) removing the cooled molded article from the sinter mold.

16. Molded article, obtainable by the method according to claim 15.

09830888-120501